WEST Search History

Hide Items | Restore | Clear | Cancel

DATE: Sunday, December 04, 2005

Hide?	Set Name	Query	Hit Count
		DB=PGPB,USPT,USOC,EPAB,JPAB,DWPI; PLUR=YES; OP=OR	
☐	L22	L21 and quench$3 and harden$2	107
☐	L21	L19 and (bearing or roller or gear) and temper$3	151
☐	L20	L19 and (bearing or roller or gear)	181
☐	L19	l7 and (carbide or nitride or carbonitride)	464
☐	L18	L17 and (bearing and roller or gear)	18
☐	L17	l7 and 420/$.ccls.	91
☐	L16	L15 and (bearing or roller or gear)	100
☐	L15	l7 and 148/3$.ccls.	277
☐	L14	l13 and (bearing or roller or gear)	19
☐	L13	l7 and 148/333.ccls.	75
☐	L12	L7 and 148/575.ccls.	3
☐	L11	L7 and 148/573.ccls.	0
☐	L10	L7 and 148/572.ccls.	2
☐	L9	L7 and 384/$.ccls.	16
☐	L8	L7 and 148/906.ccls.	12
☐	L7	steel and martensit$2 and cementite and (cr or chromium or v or vanadium)	608
☐	L6	L4 and 148/$.ccls.	69
☐	L5	L4 and 148/906.ccls.	0
☐	L4	L3 same (cr or chromium or v or vanadium)	121
☐	L3	steel same martensit$2 same cementite	421
		DB=JPAB; PLUR=YES; OP=OR	
☐	L2	L1 same (cr or chromium or v or vanadium)	13
☐	L1	steel same martensit$2 same cementite	54

END OF SEARCH HISTORY